

DURA SEAL

Polyurethane Emulsion Floor Sealer

This extraordinary water based acrylic seal concentrate is reinforced with urethane for added durability and and exceptional wear properties. DURA SEAL is especially effective on concrete and terrazzo floors. DURA SEAL has been formulated to make it less sensitive to amine based floor strippers. Floor finishes placed over this product can normally be stripped off without affecting the seal, thereby adding to the life of the surface being coated.

DURA SEAL may be applied by roller, rayon mop, or even by spraying. For best results, two coats may be applied an hour apart, and more the next day if desired. This product levels beautifully, and is capable of making even damaged surfaces appear like new. For example, terrazzo or filled travertine (marble) floors that have had run-ins with acids or other damaging chemicals appear rough or "bumpy." After preparing the surface, apply two coats of DURA SEAL. Wait 24 hours and burnish the floor dry with a 2000+ rpm burnisher. Apply two more coats, and again wait another 24 hours to burnish. This process can continue for 2 of 4 more coats if needed. The results are sensational.

SPECIFICATIONS FOR DURA SEAL

Appearance.....	Milky white emulsion
pH.....	8.5-9.5
Specific Gravity.....	1.01
Non-Volatile (solids content).....	18.0
Durability.....	Excellent
Slip Resistance.....	Exceeds 0.5 minimum average static coefficient of friction (James Machine)
Removability.....	Good, w/John-Henry® Mop-N-Strip
Coverage.....	1000 - 2000 sq. ft/gallon
Drying Time.....	30-45 minutes (under normal conditions)
Leveling.....	Very good
Minimum Application Temp.....	50° F
Storage Temperature.....	36° F minimum, 120° F maximum
Storage Stability.....	Excellent, 1 year under normal conditions

Chemical Resistance

Grease.....	No Effect	Motor Oil.....	No Effect
10% HCL.....	No Effect	Gasoline.....	Slight Softening
10% KOH.....	Slight Softening	Vinegar.....	Slight Softening
Brake Fluid.....	Slight Softening	CocaCola.....	No Effect
Ethylene Glycol..	No Effect	Xylene.....	Softening
Butyl Cellosolve..	Dissolved	Alcohol.....	Softening

HMIS RATINGS			
Health	1	Flammability	0
Reactivity	0	Personal Protection	B
PACKAGING			
55 gallon, #9213-03P			
6 gallon pail, #9213-06P			

